## ORALITE® 5700 **ENGINEER GRADE PREMIUM**

#### **Description**

5-mil\*, engineering grade, reflective film Available in 8 high-impact colors.

89# PE-coated silicone paper

#### Adhesive

Clear, solvent-based, permanent adhesive

#### Area of Use

Developed for the manufacture of long-term, outdoor, traffic control, guidance, warning and information signs as well as reflective lettering, numbers and symbols. Provides good resistance to chemicals and corrosion and excellent relfectivity in poor visibility and bad weather conditions. Special impact and scratch resistant surface that meets ASTM D 4956 specifications for Type I, Class 1 retroreflective sheeting.

#### **Technical Data**

Thickness* (without liner and adhesive)	5-mil*
Temperature resistance	Adhered to aluminum, -68°F to +179°F
Sea-water resistance (DIN 50021)	Adhered to aluminum, after 100h at 73°F, no variation
Resistance to solvents and chemicals	With expert application resistant to most oils, grease, fuels, aliphatic solvents, weak acids, salts and alkalis
Resistance to cleaning agents	Adhered to aluminum, 8 h in wash-alcalics (0,5% household cleaning agents) at room temperature and 149°F, no variation
Adhesive power* (FINAT-TM 1 after 24h, stainless steel)	3.43 lb/in film tear
Shelf life**	2 years
Application temperature	> +50°F
Minimum Life Expectancy (based on accepted application procedures on vertical surfaces)	7 years (unprinted)
Available Lengths	150' (50-yard) and 30' (10-yard)
Available Widths (in inches)	15 (punched), 24, 30, 48
Recommended Overlay Film	ORALITE® 5051
Print Compatibility	Thermal Print and Screen Print Compatible with ORALITE® 5018 Screen Printing Ink

<sup>\*\*</sup> in original packaging, at 68°F and 50% relative humidity \* average \*\*\* standard central European climate

#### **Product Data**

## ORALITE® 5700 meets the following ASTM D 4956 specifications for Type I, Class 1 retroreflective sheeting.

		Minimum coefficient of retroreflection						
Observation Angle		0.2°		0.5°		Daytime Luminance Factor (Y%)		
Entrance A	ngle	-4°	30°	-4°	30°	Minimum	Maximum	
white	010	70	30	30	15	27		
yellow	020	50	22	25	13	15	45	
orange	035	25	7	13	4	10	30	
red	030	14	6	7.5	3	2.5	15	
green	060	9	3.5	4.5	2.2	3	12	
blue	050	4	1.7	2	8.0	1	10	
brown	080	1	0.3	0.3	0.2	1	9	



# ORALITE® 5700 ENGINEER GRADE PREMIUM

### Color Specification Limits (Daytime)\*

		1		2		3		4	
		Х	у	Х	у	Х	у	Х	у
white	010	0.303	0.300	0.368	0.366	0.340	0.393	0.274	0.329
yellow	020	0.498	0.412	0.557	0.442	0.479	0.520	0.438	0.472
orange	035	0.558	0.352	0.636	0.364	0.570	0.429	0.506	0.404
red	030	0.648	0.351	0.735	0.265	0.629	0.281	0.565	0.346
green	060	0.026	0.399	0.166	0.364	0.286	0.446	0.207	0.771
blue	050	0.140	0.035	0.244	0.210	0.190	0.255	0.065	0.216
brown	080	0.430	0.340	0.610	0.390	0.550	0.450	0.430	0.390

Color Specification Limits (Nighttime)\*

		1		2		3		4		
		Х	у	Х	у	Х	у	Х	у	
white	010		no requirement							
yellow	020	0.513	0.487	0.500	0.470	0.545	0.425	0.572	0.425	
orange	035	0.595	0.405	0.565	0.405	0.613	0.355	0.643	0.355	
red	030	0.650	0.348	0.620	0.348	0.712	0.255	0.735	0.265	
green	060	0.007	0.570	0.200	0.500	0.322	0.590	0.193	0.782	
blue	050	0.033	0.370	0.180	0.370	0.230	0.240	0.091	0.133	
brown	080	0.595	0.405	0.540	0.405	0.570	0.365	0.643	0.355	

#### Note:

All ORALITE® products are manufactured within an ISO 9001:2008 controlled manufacturing environment and batch traceability is possible on the basis of the roll number.

#### IMPORTANT NOTICE

When using ORALITE® sheeting, please comply with relevant national specifications. ORAFOL recommends obtaining the current requirements from your local authority and ensure product conformance with such requirements. Please contact ORAFOL for further information.

All ORALITE® products are subject to careful quality control throughout the manufacturing process and are warranted to be of merchantable quality and free from manufacturing defects. Published information concerning ORALITE® products is based upon research which the Company believes to be reliable, although, such information does not constitute a warranty. Because of the variety of uses of ORALITE® products and the continuing development of new applications, the purchaser should carefully consider the suitability and performance of the product for each intended use, and the purchaser shall assume all risks regarding such use. All specifications are subject to change without prior notice.

Surfaces to which the material will be applied must be thoroughly cleaned from dust, grease or any contamination which could affect the adhesion of the material. Freshly lacquered or painted surfaces should be allowed to dry for at least three weeks and to completely cure respectively. The compatibility of selected lacquers and paints should be tested by the user, prior to application of the material. The self-adhesive reflective material can only be used for dry application. The low tensile strength of the material can make the removability of the reflective film more difficult. Please review applicable application information published by ORAFOL.

No warranty is given for purposes other than those listed in the Technical Datasheet or which are not processed according to ORAFOL's processing and handling instructions. The durability of the signs will depend on a variety of factors, including but not limited to substrate selection and preparation, compliance with recommended application guidelines, geographic area, exposure conditions and maintenance of the product and finished sign. Sign failures caused by the substrate or improper surface preparations are not the responsibility of ORAFOL. Please refer to the full warranty document available at <a href="https://www.orafolamericas.com">www.orafolamericas.com</a> for detailed information.

WARNING: This product contains chemicals known to the State of California to cause cancer, birth defects or other reproductive harm.

ORALITE® is a trademark of ORAFOL Europe GmbH.



techsupport-americas@orafol.com - www.orafolamericas.com